

# COREFLEX® 60

## THERMOPLASTIC WATERPROOFING MEMBRANE WITH ACTIVE POLYMER CORE

### DESCRIPTION

COREFLEX 60 is a 60 mil (1.5 mm) nominal thermoplastic membrane reinforced with a 5.0 oz weft inserted knit polyester fabric integrally bonded to an Active Polymer Core (APC). COREFLEX 60 offers the ultimate in waterproofing barrier protection technology. The barrier performance starts with a thermoplastic membrane with welded seams providing a monolithic watertight barrier layer. The thermoplastic membrane is reinforced with a weft inserted knit polyester reinforcement fabric and is produced with DuPont's Elvaloy-KEE® (Keytone Ethylene Ester), a solid phase high molecular weight ethylene interpolymer.

Unlike traditional liquid PVC plasticizers, the Elvaloy-KEE does not experience phase separation and migrate out; thus the membrane properties are maintained for long term performance. Elvaloy-KEE also provides superior chemical resistance properties. The Active Polymer Core layer is integrally bonded to the Elvaloy-KEE thermoplastic membrane. The APC layer is designed to activate with water to swell and form a positive seal. Thereby, at any unforeseen puncture or installation defect, the APC layer reacts at the breach, self-sealing to stop the water ingress. COREFLEX is the only welded thermoplastic membrane composite with this reactive, self-sealing performance feature.

### APPLICATIONS

The COREFLEX 60 waterproofing system provides waterproofing protection for structural concrete surfaces. Below-grade applications include backfilled cast-in-place concrete and masonry block foundation walls as well as property line shoring walls such as soldier pile and lagging. The membrane can be continued under the floor slab and up onto a horizontal deck to provide a continuous, uniform waterproofing system. COREFLEX 60 can be used to waterproof structures under continuous or intermittent hydrostatic pressure. COREFLEX 60 applications include: Plaza Decks, Split-Slab Deck Construction, Foundation Walls, Earth-Covered Structures, Property Line Construction, Under Slab, Tunnels and Greenroofs.

### INSTALLATION


General: Install COREFLEX 60 Waterproofing System in strict accordance with the manufacturer's installation guidelines and details using accessory products, protection and drainage layers, and overburden as specified or required. Install COREFLEX 60 with the grey APC geotextile side directly in contact with the concrete to be waterproofed. Division 3 Concrete Work should include WATERSTOP-RX® installed in all applicable horizontal and vertical concrete construction joints and around penetrations.

### PACKAGING

COREFLEX 60 is available in 54" x 50' (1.4 m x 15 m) rolls; 54" wide thermoplastic membrane with APC layer offset by 6" (150 mm) along the long roll edge.

### QUALITY INSURANCE PROGRAM

Rely on quality waterproofing products and the HydroShield Quality Assurance Program from CETCO. This program is designed to protect your building and its contents from water leaks through pre-installation planning, experienced craftsmanship, and onsite inspection backed by the strongest warranty in the industry. If it's worth building, it's worth protecting.



Typical COREFLEX 60 membrane overlap assembly with continuous thermoplastic weld

## COREFLEX® 60

### THERMOPLASTIC WATERPROOFING MEMBRANE WITH ACTIVE POLYMER CORE

TECHNICAL DATA		
PROPERTY	TEST METHOD	TYPICAL VALUE
Membrane Composite Thickness	ASTM D751	150 mil (3.8 mm)
Hydrostatic Pressure Resistance (min 1 hr @ 100 psi)	ASTM D5385	231 ft (70 m)
Puncture Resistance	ASTM D4833	224 lbs (996 N)
Tensile Strength ASTM D751	ASTM D751	549 lbs (2,442 N)
Bonded Seam Strength	ASTM D751	705 lbs (3,136 N)
Peel Adhesion to Concrete	ASTM D903 (mod)	10 lbs/in (1,751 N/m)
Methane Permeability	ASTM D1434	25 mL (STP)/m <sup>2</sup> /day
Oil Resistance	ASTM D543	Passed
Microorganism Resistance	ASTM D4068-88	Passed
Environmental Stress Cracking	ASTM D1693	Passed
Hydrostatic Resistance (Procedure A)	ASTM D751	754 psi (5.2 mPa)
Water Vapor Retarder	ASTM E1745	Class A
<i>Water Vapor Transmission</i>	ASTM E96	0.1 perms (0.036 gr/m/hr)
<i>Tensile Strength</i>	ASTM E154	387 lbf/in (68 kN/m)
<i>Puncture Resistance</i>	ASTM D1709	12.0 lbs (5,500 grams)

North America: 847.851.1800 | 800.527.9948

© 2013 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit [www.CETCO.com](http://www.CETCO.com). CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

UPDATED: SEPTEMBER 2013

TDS\_COREFLEX60\_AM\_EN\_201309\_v1



An **AMCOL** Company

[www.CETCO.com](http://www.CETCO.com)