

GEOHERMAL GROUT™

ENHANCED THERMALLY CONDUCTIVE GROUT



Certified to NSF/ANSI 60

DESCRIPTION

GEOHERMAL GROUT is a specially blended high solids bentonite that can be mixed with sand in a two-part thermally conductive grouting material to improve the performance of ground source heat loop applications. GEOHERMAL GROUT is an easy pumping grout that has been carefully developed to efficiently suspend solids (silica sand) for enhanced thermal conductivity. GEOHERMAL GROUT can be mixed to meet a range of thermal conductivity (TC) from 0.40 to 1.00 Btu/hr/ft/F (0.68 to 1.69 W/mK). GEOHERMAL GROUT is certified to NSF/ANSI Standard 60, Drinking Water Treatment Chemicals - Health Effects.

ADVANTAGES

GEOHERMAL GROUT improves the efficiency and performance of ground source heat loop systems by matching the thermal conductivity of the surrounding soil and creating a permanent flexible seal to prevent aquifer contamination. Depending on site soil conditions, GEOHERMAL GROUT can be mixed and adjusted to meet individual thermal conductivity requirements, improving the transfer of heat between the fluids circulated in the loop and the surrounding soil for optimum system performance.



TYPICAL PROPERTIES

Batch Yield	16.4 - 31.3 gal/batch (62.2 - 119.6 liters/batch)
Grout Weight	10.2 - 14.1 lb/gal (1.22 - 1.69 kg/l)
Max Particle	<300 µm
Percent Solids	30.0 - 68.0%
Permeability	<5.2x10 ⁻⁹ cm/s
Specific Gravity	2.62 g/cm ³
Thermal Conductivity	0.40 - 1.00 Btu/hr/ft/F (0.68 - 1.69 W/mK) <i>(TC values will vary depending on testing method and the quality of sand used)</i>

Btu/hr/ft/F (D-5334)	Silica lb/batch	Water gal/batch	Yield gal/batch	Weight lb/gal	Total Solids
0.40	0	14	16.4	10.2	30.0%
0.80	150	15	24.6	13.2	61.5%
0.90	200	16	28.0	13.7	65.2%
1.00	250	17	31.3	14.1	68.0%

W/mK (D-5334)	Silica kg/batch	Water l/batch	Yield l/batch	Weight kg/l	Total Solids
0.68	0	53	62	1.22	30.0%
1.36	67.5	57	93	1.58	61.5%
1.52	90	61	106	1.64	65.2%
1.69	113	64	130	1.69	68.0%

MIXING AND APPLICATION

Place freshwater in a paddle-mixing tank of a commercial grout mixer. Start the grout mixer paddle, and add one 50 lb (22.7 kg) bag of GEOHERMAL GROUT to the water. Mix for about 1 minute. Add silica sand at a steady rate (1 to 2 minutes), and continue mixing for about 2 minutes to obtain a consistent mixture. Pump with a positive displacement piston pump through a tremie pipe at a rate of 5 to 15 gallons (19 to 57 liters) per minute.

PACKAGING

50 lb (22.7 kg) bag, 48 per pallet. All pallets are plastic-wrapped.

GEOTHERMAL GROUT™ ENHANCED THERMALLY CONDUCTIVE GROUT

GEOTHERMAL GROUT Grout Volume Requirement Table					
Nominal Borehole Size (in)	U-Bend Pipe Size		Gallons of Grout/ Linear Foot with Single U-Bend (2 Pipes)	Batches/100 ft of Bore (@ 65-68% Solids)	
	Nominal O.D. (in)	Actual O.D. (in)		200 lb	250 lb
4.50	3/4	1.050	0.7362	2.78	2.49
	1	1.315	0.6851	2.71	2.43
	1 1/4	1.660	0.6013	2.54	2.26
4.75	3/4	1.050	0.8306	3.14	2.82
	1	1.315	0.7794	3.04	2.71
	1 1/4	1.660	0.6957	2.86	2.55
5.00	3/4	1.050	0.9300	3.50	3.13
	1	1.315	0.8789	3.36	3.00
	1 1/4	1.660	0.7951	3.21	2.88
	1 1/2	1.900	0.7254	3.10	2.78
5.50	3/4	1.050	1.1442	4.25	3.76
	1	1.315	1.0931	4.16	3.70
	1 1/4	1.660	1.0093	4.01	3.57
	1 1/2	1.900	0.9396	3.88	3.47
6.00	3/4	1.050	1.3788	5.07	4.53
	1	1.315	1.3277	4.92	4.40
	1 1/4	1.660	1.2439	4.85	4.34
	1 1/2	1.900	1.1742	4.76	4.21
6.50	1	1.315	1.5827	5.84	5.27
	1 1/4	1.660	1.4989	5.75	5.14
	1 1/2	1.900	1.4292	5.64	5.04

Note: U-Bend Pipe Sizes based on ASTM D-3035 and ASTM D-2447 (Polyethylene, IPS-OD)

How to use this table when using 200 lbs of sand:

Example: 100 bores, each 250 feet deep with a 5 in diameter and a 1 in U-bend assembly installed.

- Find the bore diameter on the left side of the table (5.00 in).
- Next, find the U-bend Pipe Size, Nominal O.D. in the next column (1 in).
- Looking across this row, notice these bores will require 0.8789 gallons of grout per linear foot.
- Calculate total batches of GEOTHERMAL GROUT required for each bore.
 3.21 (from the far right column) x 2.50 (250 ft deep/100) = 8.03 batches per bore
- Calculate the total batches of GEOTHERMAL GROUT required for the entire project.
 8.03 (from step 4 above) x 100 (total number of bores) = 803 total batches required

GEOTHERMAL GROUT Grout Volume Requirement Table					
Nominal Borehole Size (cm)	U-Bend Pipe Size		Liters of Grout/ Linear Meter with Single U-Bend (2 Pipes)	Batches/30 m of Bore (@ 65-68% Solids)	
	Nominal O.D. (cm)	Actual O.D. (cm)		90 kg	113 kg
11.4	1.91	2.67	9.43	2.78	2.49
	2.54	3.34	8.50	2.71	2.43
	3.18	4.22	7.47	2.54	2.26
12.1	1.91	2.67	10.31	3.14	2.82
	2.54	3.34	9.68	3.04	2.71
	3.18	4.22	8.64	2.86	2.55
12.8	1.91	2.67	11.55	3.50	3.13
	2.54	3.34	10.92	3.36	3.00
	3.18	4.22	9.87	3.21	2.88
	3.81	4.83	9.01	3.10	2.78
14	1.91	2.67	14.16	4.25	3.76
	2.54	3.34	13.58	4.16	3.70
	3.18	4.22	12.53	4.01	3.57
	3.81	4.83	11.67	3.88	3.47
15.2	1.91	2.67	17.11	5.07	4.53
	2.54	3.34	16.49	4.92	4.40
	3.18	4.22	15.45	4.85	4.34
	3.81	4.83	14.58	4.76	4.21
16.5	2.54	3.34	22.73	5.84	5.27
	3.18	4.22	18.62	5.75	5.14
	3.81	4.83	17.75	5.64	5.04

Note: U-Bend Pipe Sizes based on ASTM D-3035 and ASTM D-2447 (Polyethylene, IPS-OD)

How to use this table when using 90 kg of sand:

Example: 100 bores, each 75 m deep with a 12.8 cm diameter and a 2.54 cm U-bend assembly installed.

- Find the bore diameter on the left side of the table (12.8 cm).
- Next, find the U-bend Pipe Size, Nominal O.D. in the next column (2.54 cm).
- Looking across this row, notice these bores will require 0.8789 gallons of grout per linear meter.
- Calculate total batches of GEOTHERMAL GROUT required for each bore. 3.21 (from the far right column) x 2.50 (75 m deep/30 m) = 8.03 batches per bore
- Calculate the total batches of GEOTHERMAL GROUT required for the entire project.
 8.03 (from step 4 above) x 100 (total number of bores) = 803 total batches required

GEOHERMAL GROUT™ **ENHANCED THERMALLY CONDUCTIVE GROUT**

SAND REQUIREMENTS

In order to comply with GEOHERMAL GROUT specifications, the silica sand used must meet the following criteria. To minimize freight cost it is recommended that the sand portion be obtained locally for most projects, following the sand specifications above for grain mesh size. GEOHERMAL GROUT can be used with a wide variety of sand sizes. Some suggested specifications are listed below.

Silicon Dioxide: 99%	Grain Shape: Rounded		Moisture: <0.1%
Sieve Mesh Size	Retained %	Cumulative %	Passing %
#40	1.0% maximum	1.0% or less	99.0%
#50	23.0%	23.0%	77.0%
#70	57.0%	80.0%	20.0%
#100	15.0%	95.0%	5.0%
#140	3.0%	98.0%	2.0%
<#140	2.0%	100.0%	0.0%

GEOTHERMAL GROUT™ ENHANCED THERMALLY CONDUCTIVE GROUT

GEOTHERMAL GROUT TEST POLICIES

THERMAL CONDUCTIVITY (TC)

TC testing as required can be performed in the CETCO Laboratory free of charge for the distributor or contractor purchasing GEOTHERMAL GROUT.

- a) CETCO will perform the testing using ASTM D-5334 - *Determination of Thermal Conductivity of Soil and Soft Rock by Thermal Needle Probe Procedure*. Testing using ASTM C-518 - Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus, can be performed at an outside test facility for an additional charge.
 - b) The sample container(s) shall be a minimum of four inches in diameter by at least five inches deep.
 - c) The container should be completely filled to the top and covered to prevent moisture loss.
 - d) The container should be rigid to semi-rigid and packaged appropriately so no disturbance takes place when shipped for analysis.
 - e) CETCO can provide the contractor with a list of laboratories qualified to conduct the TC testing according to acceptable ASTM standards.
 - f) Test results will be reported as they become available to the supervising engineer, the installation contractor, and CETCO.
 - g) CETCO will not be financially responsible for charges billed by independent laboratories and charges will be billed directly to the supervising engineering firm, CETCO distributor, or installation contractor.
- c) Quality of the sand will be analyzed to confirm silica content, roundness, and size.
 - d) CETCO will mix the sand into a lab batch with GEOTHERMAL GROUT using the same proportions of sand typically required to achieve the thermal conductivity (TC) desired.
 - e) TC testing results will determine the quantity of sand required for the job specification.
 - f) Results and recommended mix proportions will then be reported to the responsible party.

PERMEABILITY TESTING

Permeability testing as required can be performed in the CETCO Laboratory for a fee per sample for the distributor or contractor purchasing the GEOTHERMAL GROUT.

- a) CETCO will perform the testing using ASTM D-5084 - *Measurement of Hydraulic Conductivity of Saturated Porous Materials Using a Flexible Wall Permeameter*.
- b) The sample(s) shall be a minimum of five inches in diameter and two inches deep and covered prior to shipment.
- c) Sample container should be rigid to semi-rigid in construction.
- d) If independent testing is required, CETCO can provide the contractor with a list of qualified laboratories.
- e) Test results will be reported as they become available to the supervising engineer, the installation contractor, and CETCO.
- f) CETCO will not be financially responsible for charges billed by independent labs and charges will be billed directly to the supervising engineering firm, CETCO distributor, or installation contractor.

SAND

Sand quality has a direct effect on the TC achieved by enhanced bentonite grouts. Sand quantity needed may vary depending on characteristics. CETCO suggests that sand being considered for enhancing the thermal conductivity of GEOTHERMAL GROUT be submitted to CETCO for laboratory analysis prior to commencement of the project. This service is free of charge for the distributor or contractor purchasing the GEOTHERMAL GROUT. TC testing as required can be performed in the CETCO laboratory free of charge for the distributor or contractor purchasing the GEOTHERMAL GROUT. The following procedures and policies should be adhered to in order to achieve desired results.

- a) Sand samples should be sent directly to the CETCO laboratory by the manufacturer.
- b) Sand should be accompanied by a description and sieve analysis from the manufacturer.

North America: 847.851.1800 | 800.527.9948

© 2013 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

UPDATED: DECEMBER 2013

TDS_GEOTHERMALGROUT_AM_EN_201311_v1

CETCO®

An **AMCOL** Company

www.CETCO.com