



TexDrain™ 250 SS 12 Certified Properties

TD 250 SS 12 is a superior quality composite drainage product produced by thermally laminating a 12 ounce per square yard nonwoven geotextile to a core of high-flow polyethylene drainage net. TexDrain Geocomposites are designed to provide high capacity planar flow of liquids, with integrated protection from clogging and damage protection for adjacent geomembranes.

TD 250 SS 12 and individual components conform to the physical property values listed below:

250 mil GEONET PROPERTIES	TEST METHOD	UNITS	VALUE
Thickness	ASTM D 5199	mils	250
Polymer Density	ASTM D 1505	g/cm ³	0.940
Transmissivity ¹	ASTM D 4716	g/min/ft (m ² /s)	7.2 (1.5x 10 ⁻³)
Carbon Black	ASTM D 1603	%	2
Tensile Strength	ASTM D 5035	lbs/in	60

¹ - Transmissivity measured in the machine direction using water at 20 Degrees C (68 degree F) with a gradient of one, under a confining pressure of 10,000 psf, between two steel plates, after 15 minutes. Values may vary based on dimension of the transmissivity specimen and specific laboratory.

GEOTEXTILE PROPERTIES ²	TEST METHOD	UNITS	VALUE
Weight	ASTM D 5261	oz/yd ²	12
Grab Tensile	ASTM D 4632	lbs	310
Tear Strength	ASTM D 4533	lbs	120
Puncture	ASTM D 4833	lbs	180
Permittivity	ASTM D 4491	Sec ⁻¹	0.8
AOS	ASTM D 4751	US Sieve	100 sieve
UV Stability	ASTM D 4355	% retained (500 hr)	70

² - Prior to lamination to geonet core. Thermal lamination may alter these properties. Geotextile properties are Minimum Average Roll Values, except for AOS, which is Maximum Average Roll Value.

GEOCOMPOSITE PROPERTIES	TEST METHOD	UNITS	VALUE
Transmissivity ³	ASTM D 4716	g/min/ft (m ² /s)	1.0 (2.0 x 10 ⁻⁴)
Peel Adhesion	ASTM D 7005	lbs/in	1

³ - Transmissivity measured in the machine direction under a gradient of one, under a confining pressure of 10,000 psf, between two steel plates, after 15 minutes. Values may vary based on dimension of the transmissivity specimen and specific laboratory.

ROLL DIMENSIONS ⁴	WIDTH	LENGTH	AREA	WEIGHT
	13.5 feet	225 feet	3,037.5 ft ²	963 lbs

⁴ - Weight is nominal. Length subject to change based on optimized shipping dimensions.



TR-723
Revised 6/05

1500 West Shure Drive Arlington Heights, IL 60004 USA 800.527.9948 Fax 847.577.5566
For the most up-to-date product information please visit our website, www.cetco.com
A wholly owned subsidiary of AMCOL International Corporation

The information and data contained herein are believed to be accurate and reliable, CETCO makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.