

CETGUARD METAL PRIMER

SINGLE-COMPONENT PRIMER

DESCRIPTION

CETGUARD METAL PRIMER is a high performance solvent-borne polymer-based 1-component primer.

PRODUCT USE

CETGUARD METAL PRIMER is used as a coupling agent for various metal substrates in conjunction with CETCO roofing, waterproofing and surfacing systems. CETGUARD METAL PRIMER should be used in applications with higher mechanical stresses (e.g., trafficked areas), on detail work with small contact areas, metal drain bowls, or edge terminations metal.

PACKAGING

CETGUARD METAL PRIMER is supplied in 1.0-kg cans.

COVERAGE RATE (APPROXIMATE)

Consumption: 0.17 – 0.2 kg/m²

Gross yield / 1.0-kg unit: ± 5 m² (54 ft²) – ± 5.9 m² (63 ft²) depending upon substrate conditions and consumption at application.

STORAGE

Always store in cool and dry location, protected from frost. Do not store in direct sunlight or in temperatures below 0°C (32°F) or above 25°C (77°F). Approximate shelf life is 6-months when left sealed, un-opened and with proper storage.

APPLICATION CONDITIONS

The normal recommended temperature range for application of this product is (ambient and substrate) between 3°C (37°F) and 35°C (95°F).

Application over CETGUARD METAL PRIMER should be done following the recommended minimum cure times indicated up to a maximum of 24-hours. If the surface of the primer becomes dirty or contaminated or left exposed to the elements for more than 24-hours, the primer must be ground off and re-applied.

Note: Galvanized and zinc rich metals are typically passivated or coated with oil requiring special preparation. The passivator must be completely removed by mechanical abrasion for CETGUARD METAL PRIMER to obtain sufficient long-term bond. This can be confirmed by applying a coat of copper sulfate solution to the prepared galvanized metal surface. A properly prepared surface will turn black indicating the passivator has been removed. If the surface does not turn black, additional abrasive cleaning will be required. In certain applications with zinc rich or stainless steel metals, an acceptable pre-primer may be required prior to application of CETGUARD METAL PRIMER. Consult CETCO Technical Department for recommendations regarding specific applications.

MIXING INSTRUCTIONS

CETGUARD METAL PRIMER must be stirred before use. CETGUARD METAL PRIMER does not need to be catalyzed prior to application.

SUBSTRATE PREPARATION

Mask perimeter and top edge of the area to be primed and flashed to provide clean lines and prevent overpainting of resins. Prepare metal surfaces to near white metal, abraded, and wipe clean with CETGUARD ACTIVATOR. Extend preparation a maximum of 3 mm (1/8") beyond the termination of the membrane flashing.

CURE TIMES

- 30°C (86°F): at least 1-hour
- 20°C (68°F): at least 2-hours
- 10°C (50°F): at least 3-hours
- 3°C (37°F): at least 4-hours

The times noted above are approximate, provided as a guideline, and may vary. Actual set times and cure should be established in the field based on actual field conditions.

TOOL CLEANING

When work is interrupted or completed, tools must be thoroughly cleaned with CETGUARD ACTIVATOR before the resin hardens.

SAFETY RECOMMENDATIONS

Refer to product Safety Data Sheet (SDS) prior to use or handling.

DISPOSAL

Cured resin may be disposed of in standard landfills. Uncured resin is considered a hazardous material and must be handled as such, in accordance with local, state and federal regulations.

CETGUARD METAL PRIMER SINGLE-COMPONENT PRIMER

APPLICATION GUIDELINES

HANDLING

Keep away from open fire, flame or any ignition source. Vapors may form explosive mixture with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink or smoke in area of application. Refer to product Safety Data Sheet (SDS) for additional information pertaining to this product and prior to use or handling.

PERSONAL PROTECTION EQUIPMENT

Workers should wear appropriate clothing to protect from accidental skin contact. When mixing or applying this product workers must use butyl rubber or nitrile gloves. Safety glasses with side shields are required for eye protection.

In enclosed spaces, use local exhaust ventilation to maintain worker exposure below the Threshold Limit Level (TLV). If the airborne concentration poses a health hazard, become irritating or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. The specific type of respirator will depend on the airborne concentrations. A filtering face piece or dusk mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

SURFACE PREPARATION

All substrates must be clean, dry, free of oil, grease, foreign material such as dirt, ice, snow, water or any other condition that would be detrimental to adhesion of resin to the substrate. Mask perimeter and top edge of the area to be primed and flashed to provide clean lines and prevent over-painting of resins. Apply CETGUARD METAL PRIMER to substrate as recommended. Remove and re-apply masking before primer cures and as required between coats. Refer to TR_CG_106 "CETGUARD Substrate Preparation Guidelines" for specific recommendations and requirements. Contact CETCO for recommendations regarding specific applications.

APPLICATION

After mixing, apply resin to clean and prepared substrate at the required consumption using CETCO approved rollers or brushes. The resin should be spread evenly onto the surface. See individual system specifications for specific guidelines regarding application of primer, membrane, and topcoat.

REMARKS/COMMENTS

The information provided regarding application of CETCO products is based on extensive development work, as well as many years of experience, and is given to the best of our knowledge. However, due to the diverse conditions encountered in building construction, it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make alterations in keeping with technical developments or improvements.

DISCLAIMER

NO WARRANTY, EXPRESS OR IMPLIED, IS MADE IN THIS DOCUMENT. THE PRODUCT IS NOT CLAIMED TO BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. User and certified CETCO Approved Applicators determine suitability only. See individual CETCO product data sheets, SDS sheets, guide specifications and details for complete information regarding the suitability, application and handling of CETCO products.

North America: cetco@mineralstech.com | www.cetco.com

UPDATED: MARCH 2025 (Supersedes all previous versions)

© 2025 Minerals Technologies Inc. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.cetco.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

FORM: TDS_CETGUARD_METAL_PRIMER_AM_EN_202503_V1

CETCO
A MINERALS TECHNOLOGIES COMPANY